DECLARATION OF PERFORMANCE

DoP Nr. 741 rev. 4


Type:

HELUZ FAMILY 30 grinded brick

1. Unique identification code of the product-type: **57305.00**

2. Intended use:

for protected load-bearing and non-load-bearing walls



The grawing is indicative and may be modified slightly

3. Manufacturer:

HELUZ s.r.o. U Cihelny 295, CZ 373 65 Dolní Bukovsko I : 28068262

Factory: Hevlin II.

- 5. System of assessment and verification of constancy of performance of the construction product: System 2+
- 6a. Harmonised standard: EN 771-1:2011+A1:2015; Notified body/ies: 1020 TZÚS Praha, s.p.
- 7. Declared performance:

Essential characteristic			Performance		Harmonized technical specification
Compressive strength (^ bedface)*,		mean	10	N/mm²	
Category I, P		normalized	11,5		EN 771-1:2011+A1:2015
Dimensional stability		moisture movement	NPD	mm/m	
Active soluble salts content			NPD (S0)		
Reaction to fire			Euroclass A1		
Water absorption		Not to be left exposed!			
Direct airborne sound insulation		wall with the both side plaster	NPD	dB	
Gross dry density		category of tolerance	670	kg/m3	
Work dimensions	Length:	dimensional tolerance and	247	m m	
	Width:	range category Tm		m m	
	Height:	R2+	249	mm	
Flatness of bed faces			- 0,1	m m	
Plane parallelism of bed faces			0,4	m m	
Group of masonry units		vertically perforated element with a tongue and groove system, group 3 in accordance with EN 1996-1-1, see attached picture			
Bond strength (for elements intended for use in load-bearing structures)		determined value	0,3	N/mm²	EN 998-2:2016
Water vapor permeability		Diffusion resistance factor	5/10		EN 1745:2012

Essential charac	Performance		Harmonized technical specification	
Thermal conductivity 10,dry, unit	Method P5	0,088	W/mK	EN 1745:2012
Durability against freeze-thaw	Not to be left exposed!	NPD (F0)		EN 771-1:2011+A1:2015
Hazardous substances	Mass activity ²²⁶ Ra < 120 Bq.kg ⁻¹			

Next characteristics Acoustic brick

The minimum thickness of the face side shells is	Minimum area for concrete infill canal is		
NPD	mm - mm2		
and of the perpend shell is	mm and its smallest dimension is - mm		
The minimum thickness of the webs is	The average volume of the recess (mortar pockets) is		
NPD	mm - <i>ml</i>		
Percentage of voids is	Percentage of grip hole is		
	-%		

The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above. Signed for and on behalf of the manufacturer by:

Ing. Jan Smola Proxy holder

Dolní Bukovsko 12.05.2017

^{*} Test according to EN 772-1, treating compressed areas according to article 7.2.4 and conditioning according to article 7.3.2. A single strength value is not less than 0.8 times of the declared compressive strength.

^{**} T_m: At the calibrated bricks is the maximum height difference +/- 0.5 mm. The dimensional tolerance category of width and length is T2 +.